

ZINC

UNS ^B	Fe	Pb	Cd	Cu	Mg	Sn	As	Al	Sb ^C	Others, Total	Zn ^D
Type A-1 90/10 Zn/Al Z30750	0.05 max	0.005 max	0.004 max	0.035 max	...	0.003 max	...	9.5–10.5	...	0.01 max	Remainder
Type A-2 90/10 Zn/Al Z31710	0.15 max	0.4 max	...	0.5 max	9.5–10.5	...	0.25 max	Remainder
Type A-3 95/5 Zn/Al Z30503	0.05 max	0.005 max	0.004 max	0.035 max	...	0.003 max	...	4.5–5.5	...	0.01 max	Remainder
Type A-4 95/5 Zn/Al Z31510	0.15 max	0.4 max	...	0.5 max	4.5–5.5	...	0.25 max	Remainder
Type A-5 96/4 Zn/Al ZXXXXX	0.05 max	0.0005 max	0.004 max	0.035 max	0.06 max	0.003 max	...	4.0–4.5	...	0.01 max	Remainder
Type A-6 96/4 Zn/Al ZXXXXX	0.15 max	0.4 max	...	0.5 max	0.06 max	4.0–4.5	...	0.25 max	Remainder
Type S-1 90/10 Zn/Sb Z55710	0.03 max	0.015 max	0.003 max	0.003 max		0.01 max	0.015 max	...	9.5–10.5	0.03 max	Remainder
ALLOY	Si	Fe		Cu	Mn	Mg	Ni	Zn	Sn	Ti	Pb
ZL101A	6.5-7.5	0.2MAX		0.1MAX	0.1MAX	0.25-0.45		0.1MAX	0.01MAX	0.08-0.2	0.03MAX
ZL102	10.0-13.0	0.7MAX		0.3MAX	0.5MAX	0.1MAX		0.1MAX		0.2MAX	
ZL104	8-10.5	0.6MAX		0.1MAX	0.2-0.5	0.17-0.30	0.2-0.5	0.25MAX	0.01MAX	0.15MAX	0.05MAX
ZL106	7.5-8.5	0.6MAX		1.0-1.5	0.3-0.5	0.3-0.5		0.2MAX	0.01MAX	0.1-0.25	0.05MAX
ZL107	6.5-7.5	0.5MAX		3.5-4.5	0.5MAX	0.1MAX		0.3MAX	0.01MAX		0.05MAX
ZL108	11.0-13	0.7MAX		1.0-2.0	0.3-0.9	0.4-1.0	0.3MAX	0.2MAX	0.01MAX	0.2MAX	0.05MAX
ZL109	11.0-13	0.7MAX		0.5-1.5	0.2MAX	0.8-1.3	0.8-1.5	0.2MAX	0.01MAX	0.20MAX	0.05MAX
ZL201	0.3MAX	0.3MAX		4.5-5.3	0.6-1.0	0.05MAX	0.1MAX	0.2MAX		0.15-0.35	